

TEST PARAMETER

Nordikka[®]
— COMMERCIAL LVT —

CHARACTERISTICS	TEST METHOD	RESULT
Dimension	EN 427	185x1229mm
Thickness-Overall	EN 428	2.5mm
Thickness-Wear Layer	EN 429	0.55mm
Total Weight	EN 430	4.90kg/m ²
Caster Wheel Chair	EN 425	Pass
Abrasion Resistance	EN 660-2	T grade
Indentation Residual	EN 433	Pass
Colour Fastness	EN ISO 105-BO2	≥6
Fire Rating	EN13501-1	B _{fl} -s1
Effects of Stain	EN 423	Pass
Residual Indentation after Stability	EN 434	Shrinkage≤0.08% Curling≤2.0mm
Peeling Strength of Layers	EN 431	Pass
Flexibility-10mm Mandrel	EN 435	No Damage
Resistance to Chemicals	EN 423	Class 0
Toxic	EN 71Part3	Pass
Slip Resistance	DIN 13893	R10
Performance Classification	EN 685	23/34/43
GB/T 4085 GB 86t24 B1		Pass
CNS 8907		Pass
Impact Sound Reduction	ISO 10140-3	2db
Impact Insulation Class(IIC)	ASTM E90/492	IIC36
Sound Transmission Coefficient	ASTM E90/492	STC 55

Suitable for use with underfloor heating up to 27°C

Wear guarantee:
Lifetime Residential
15 Years Commercial

